



240 gr/m², 100% Polyester,
Wind Jacket Fabric



Sample



Description

100% Polyester wind jacket fabric. ArMoto can be used on motorcyclist cloths as air channel.
For the shoes industry it is popular fabric to laminate on base and edge of sport shoes.

Technical Parameters

| Name | Values | Standards |
|-----------------------|---------------------------------|----------------|
| Fiber | 100% Polyester (PES) | TS EN ISO 1833 |
| Yarn | 300 Denier | EN ISO 2060 |
| Weight | 240 ±5 gr/m ² | TS EN 12127 |
| Width | 1500 ±20 mm | TS EN 1773 |
| Bursting strength | > 2500 kPa (kN/m ²) | TS EN 13938-1 |
| Dimensional Change | -5%<Length<+5%;-5%<Width<+5% | TS EN ISO 5077 |
| Abrasion Resistance | @50000 | TS EN 530 |
| Rubbing Fastness | 4 | EN ISO 105 X12 |
| Perspiration Fastness | 4-5 | EN ISO 105 E04 |
| Washing Fastness | 4-5 | EN ISO 105 C01 |
| Dry Cleaning Fastness | 4-5 | EN ISO 105 D01 |
| Hypochlorite Fastness | 4-5 | EN ISO 105 N01 |
| Hot Press Fastness | 4-5 | EN ISO 105 X11 |
| Light Fastness | 4-5 | EN ISO 105 B02 |
| pH | 6.2 | EN ISO 3071 |
| Azo Test | No Azo Colorants. | EN ISO 14362-1 |
| Application | Wind Jacket, Shoes | |
| Quality Management | Done | ISO 9001 |

ArMoto - 4349
Navy



ArMoto - 4350
Black

