



**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU

16032006

07-16

EKOTEKS

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Velimeşe OSB Mah. Hacı Şeremet 5. Sokak 9/9 ERGENE/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: -
Name and identity of test item: One sample of (claimed to be 100% Cotton; Grey Woven Fabric) grey woven fabric.
The date of receipt of test item: 13.07.2016
Re-submitted/re-confirmation date: -
Date of test: 13.07.2016-15.07.2016
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.
Number of pages of the report: 3



Date
15.07.2016

Customer Representative
N. Fisun EROL

Head of Testing Laboratory
Seyim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.


16032006

07-16

REQUIRED TESTS	RESULT	COMMENTS
COLOUR FASTNESS TESTS		
Colour Fastness to Chlorine Bleach	-	

No requirement was given by vendor.

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

16032006

07-16

TEST RESULTS

COLOUR FASTNESS TO:

CHLORINE BLEACH; TS 739 EN 20105 N01:1999(*)
Evaluated with ISO 105 A02 grey scale for colour change assesment.

	<u>RESULT</u>	<u>REQUIREMENT</u>
Colour Change	4	-

COLOUR FASTNESS RATING

	COLOUR CHANGE
5	Negligible or no change
4	Slightly changed
3	Noticeably changed
2	Considerably changed
1	Much changed

	COLOUR STAINING
5	Negligible or no staining
4	Slightly stained
3	Noticeably stained
2	Considerably stained
1	Much stained