



**TÜRKAK**  
**TÜRK AKREDİTASYON KURUMU**  
**TURKISH ACCREDITATION AGENCY**  
*tarafından akredite edilmiş*

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**  
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**TEST REPORT**  
**DENEY RAPORU**



AB-0583-T

16032009

07-16

**Customer name:** ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.  
**Address:** Velimeşe OSB Mah. Hacı Şeremet 5. Sokak 9/9 ERGENE/ TEKİRDAĞ  
**Buyer name:** -  
**Contact Person:** ÖZGÜR KUŞKU  
**Order No:** -  
**Article No:** -  
**Name and identity of test item:** One sample of (claimed to be 100% Cotton; Grey Woven Fabric) grey woven fabric.  
**The date of receipt of test item:** 13.07.2016  
**Re-submitted/re-confirmation date:** -  
**Date of test:** 13.07.2016-14.07.2016  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** Not specified.  
**Number of pages of the report:** 3

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.*

Seal

Date  
14.07.2016

Customer Representative  
N. FİSUN EROL

Head of Testing Laboratory  
Sevim A. RAZAK


This report shall not be reproduced other than in full except with the permission of the laboratory.  
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T
16032009
07-16

REQUIRED TESTS	RESULT	COMMENTS
<b>COLOUR FASTNESS TESTS</b>		
Colour Fastness to Hot Pressing	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor  $k=2$ , providing a level of confidence of approximately 95 %. Tests marked (\*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

16032009

07-16

**TEST RESULTS**

**COLOUR FASTNESS TO:**

**HOT PRESSING; TS 472 EN ISO 105 X11:2000**

Atlas Scorch Tester. 150 ±2 °C. 15 seconds

ISO 105 F02-Cotton adjacent fabrics were used.

Performed in the conditioned room (20±2°C-65%±4)

Evaluated with ISO 105 A02 and ISO 105 A03 standart grey scale.

<b>Before conditioning</b>	<b><u>Colour change</u></b>	<b><u>Staining</u></b>	<b><u>REQUIREMENT</u></b>
Dry	4-5	-	-
Steamy Press	4-5	4-5	-
Wet	4	4-5	-
<b>After conditioning</b>			
Dry	4-5	-	-
Steamy Press	4-5	4-5	-
Wet	4-5	4-5	-

**COLOUR FASTNESS RATING**

**COLOUR CHANGE**

5	Negligible or no change
4	Slightly changed
3	Noticeably changed
2	Considerably changed
1	Much changed

**COLOUR STAINING**

5	Negligible or no staining
4	Slightly stained
3	Noticeably stained
2	Considerably stained
1	Much stained