

TÜRKAK
TÜRK AKREDİTASYON KURUMU
TURKISH ACCREDITATION AGENCY
tarafından akredite edilmiş

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU



AB-0583-T

16032017

07-16

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Velimeşe OSB Mah. Hacı Şeremet 5. Sokak 9/9 ERGENE/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: -
Name and identity of test item: One sample of (claimed to be 100% Cotton; Grey Woven Fabric) grey woven fabric.
The date of receipt of test item: 13.07.2016
Re-submitted/re-confirmation date: -
Date of test: 13.07.2016-15.07.2016
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.
Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.



Date
15.07.2016

Customer Representative
N. FİSİNEROL

Head of Testing Laboratory
Sevim A. RAZAK


This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
16032017
07-16

REQUIRED TESTS	RESULT	COMMENTS
COLOUR FASTNESS TESTS		
Colour Fastness to Rubbing	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

16032017

07-16

TEST RESULTS

COLOUR FASTNESS TO:

RUBBING; TS EN ISO 105 X12:2006

Performed in the conditioned room(20±2°C-65%±4)Finger type:Cylindrical
Downward force : 9±0.2 NWater absorption rate of rubbing cloth : 95 % - 100 %
Evaluated with ISO 105 A03 standart grey scale for staining assessment.

RESULT

Dry
Wet

4-5
4

REQUIREMENT

-

-

COLOUR FASTNESS RATING

COLOUR CHANGE

- | | |
|---|-------------------------|
| 5 | Negligible or no change |
| 4 | Slightly changed |
| 3 | Noticeably changed |
| 2 | Considerably changed |
| 1 | Much changed |

COLOUR STAINING

- | | |
|---|---------------------------|
| 5 | Negligible or no staining |
| 4 | Slightly stained |
| 3 | Noticeably stained |
| 2 | Considerably stained |
| 1 | Much stained |