

AR Astar Sotina

Woven lining fabrics



 1975
ARITEKS
FUNCTION FOR FLEXIBLE FABRICS

Phone: +90 212 538 05 98

Fax: +90 212 537 08 46

E-Mail: support@ariteksinfo.com

Web: www.ariteks.net




Ariteks, founded as family owned business in 1975, is the leading textile manufacturer company both in fashion and technical textiles.

By continuously developing high-end technologies it provides solutions to end users in apparel, protective workwear, functional sport, medical wear as well as technical textiles in construction and transportation industries.

As the pioneer company in special dyeing methods like indigo, vat, space-dye, coating and laminating systems, Ariteks produces highest-quality fabrics both for international and domestic markets.

Ariteks uses clean and renewable energy resources. It consumes minimum amount of water by using continuous optimised systems.

Based in 4000m² with 12 separate in house R&D laboratories, the company spends 5% of its budget for research and developing future technologies. It focuses especially on 3rd generation solar cells on flexible fabrics and biosensing textiles.



CONTENT

1	ArAstar 60 gr/m ² , 100% Polyester, 1/1 Plain Woven Fabric	4-5
2	ArSotina 140 gr/m ² , 100% Polyester, 1/1 Plain Woven Fabric	6-7



60 gr/m², 100% Polyester,
1/1 Plain Woven Fabric



Sample




ArAstar - 5652 Grey**ArAstar - 5649 Navy****ArAstar - 5461 Black****ArAstar - 5462 White**

Description

ArAstar, 100% Polyester taffeta fabric for garment lining. It can be used as a lining inside of the shoes. ArAstar is the most economical woven fabric on the market as textile material.

Technical Parameters

Name	Values	Standards
Fiber	100% Polyester	EN ISO 2076
Yarn	75 Denier	EN ISO 2060
Weight	60 ±10 gr/m ²	EN ISO 3081
Width	1500 ±20 mm	EN ISO 3932
Tensile Strength	Warp>500N; Weft>400N	EN ISO 13934-1
Tear Strength	Warp>20N; Weft>15N	EN ISO 13937-2
Dimensional Change	-3%<Length<+3%;-3%<Width<+3%	EN ISO 5077
Rubbing Fastness	4-5	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C06
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Hot Press Fastness	4-5	EN ISO 105 X11
pH	4,0 - 7,5	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Lining	
Quality Management	Done	ISO 9001



140 gr/m², 100% Polyester,
1/1 Plain Woven Fabric




Sample



ArSotina - 5909 Black



ArSotina - 5911 Navy

ArSotina - 5912
High Visible GreenArSotina - 5913
High Visible Orange

The technical data on this guide is given for information and correct at the time of design. It can be changed without prior notice.

Description

ArSotina, 100% Polyester sotina fabric for garment lining. It can be used as a lining inside of the shoes. ArSotina is a durable lining fabric for more hard conditions.

























Technical Parameters

Name	Values	Standards
Fiber	100% Polyester	EN ISO 2076
Yarn	75 Denier	EN ISO 2060
Weight	140 ±10 gr/m ²	EN ISO 3081
Width	1500 ±20 mm	EN ISO 3932
Tensile Strength	Warp>800N; Weft>800N	EN ISO 13934-1
Tear Strength	Warp>30N; Weft>25N	EN ISO 13937-2
Dimensional Change	-3%<Length<+3%;-3%<Width<+3%	EN ISO 5077
Rubbing Fastness	4-5	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C06
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Hot Press Fastness	4-5	EN ISO 105 X11
pH	4,0 - 7,5	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Lining	
Quality Management	Done	ISO 9001

Fashion Fabrics



Technical Fabrics

  BUILDING	  HOME	  PROTECTION	  MEDICAL	  SPORT	  TRANSPORT
  GEOLOGY	  PACKAGE	  CLOTH	  AGRICULTURE	  ENVIRONMENT	  MACHINE

Headquarters

Hekimsuyu Cad. No:36
 Kucukkoy/Gaziosmanpasa 34250 Istanbul/Turkey
 Phone: +90 212 538 05 98-99
 E-Mail: support@aritekinfo.com
 Web: www.aritek.net

Factory

Velimese OSB Mah. 210. Sokak No:9/8
 Ergene 59930 Tekirdag / Turkey
 Phone: +90 282 676 41 90
 E-Mail: support@aritekinfo.com
 Web: www.aritek.net