



210 gr/m<sup>2</sup>, 93% m-Aramid  
5% p-Aramid 2% Carbon,  
Inherent Flame Retardant,  
Antistatic, Denim Fabric



## Sample



**Aramid D1 210 Denim - 5807  
Navy**

**Aramid D1 210 Denim - 5808  
Grey**


## Description

Aramid denim fabric consisting of 210 gr/m<sup>2</sup>, 93% m-Aramid, 5% p-Aramid, 2% Carbon.  
 Inherent flame retardant fabric for electricity distribution companies and oil and gas industry workers.  
 Inherent flame retardant fabric with EN ISO 11612 and EN ISO 11611 certification.  
 Antistatic (EN 1149-5) certified. Protection against thermal hazards of electrical arc (EN 61482-1-2).  
 Resistant to most industrial chemicals (EN ISO 13034).

## Technical Parameters

Name	Values	Standards
Fiber	93% m-Aramid (m-AR) 5% p-Aramid (p-AR) 2% Carbon (CF)	EN ISO 2076
Yarn	Warp:30/2Ne; Weft:30/2Ne	EN ISO 2060
Weight	210 ±5 gr/m <sup>2</sup>	EN ISO 3081
Width	1600 ±20 mm	EN ISO 3932
Tensile Strength	Warp>1500N; Weft>1000N	EN ISO 13934-1
Tear Strength	Warp>70N; Weft>60N	EN ISO 13937-2
Dimensional Change	-3%<Length<+3%;-3%<Width<+3%	EN ISO 5077
Rubbing Fastness	4-5	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C06
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Peroxide Fastness	4-5	EN ISO 105 N02
Hot Press Fastness	4-5	EN ISO 105 X11
Light Fastness	4-5	EN ISO 105 B02
Perspiration Light Fast.	4-5	EN ISO 105 B07
pH	4.0-7.5	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Electricity distribution	
Quality Management	Done	ISO 9001
Flame and Heat Protection	Yes	EN ISO 11612
Antistatic	Yes	EN ISO 1149-5
Chemical Resistant	Yes	EN ISO 13034
Arc Protection	Class 1 (4kA)	EN ISO 61482-1-2
ATPV	> 7 cal/cm <sup>2</sup>	EN ISO 61482-1-1
Welding Protection	Yes	EN ISO 11611