


210 gr/m²,
97% AriPam 3% Elasthane,
Ripstop Woven Fabric



Sample



AriRipstop El - 6008
GreyAriRipstop El - 6009
GreenAriRipstop El - 6010
Ranger

The technical data on this guide is given for information and correct at the time of design. It can be changed without prior notice.

Description

97% AriPam 3% Elasthane ripstop fabric. It is used mostly for outdoor wear as pants. AriRipstop can also be used for workwear stretchable raincoats.

Technical Parameters

Name	Values	Standards
Fiber	97% AriPam 3% Elasthane (EI)	EN ISO 2076
Yarn	40/2 Ne	EN ISO 2060
Weight	210 ±10 gr/m ²	EN ISO 3081
Width	1400 ±20 mm	EN ISO 3932
Tensile strength	Warp> 1800N; Weft>1200N	EN ISO 13934-1
Tear strength	Warp> 35N; Weft>40N	EN ISO 13937-2
Dimensional Change	-3%<Length<+3%;-3%<Width<+3%	EN ISO 5077
Rubbing Fastness	4-5	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C06
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Hot Press Fastness	4-5	EN ISO 105 X11
pH	4.0-7.5	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Outdoor Elastic Pants	
Quality Management	Done	ISO 9001